

94 - Tarkett Floorcovering - Technical Specification

A comprehensive range of resilient floorcoverings available in both sheet and tile options, offering Specifiers high performance together with design opportunities for every application.

Homogeneous Floorcoverings	Manufacturing Standard	Tiles (mm)	Sheet Width (m)	Thickness (mm)	Wear Layer Thickness (mm)	Weight (kg/m ²)	Abrasion Class EN660-2	Indentation (mm) EN433	Fire Performance EN13501-1	Wear Classification EN685	PUR Reinforcement
Eclipse Premium	EN 649	610 x 610	2	2.0	2.0	3.15	P	0.06	Bfl-s1	34.43	XR PUR
Vylon Plus	EN 649	610 x 610 300 x 300	2	2.0	2.0	3.7	M	0.06	Bfl-s1	34.43	PUR
Contract Plus	EN 649	-	2	2.0	2.0	3.25	P	0.03	Bfl-s1	34.43	PUR
IQ Granit	EN 649	610 x 610	2	2.0	2.0	3	P	0.03	Bfl-s1	34.43	IQ PUR
IQ Optima	EN 649	610 x 610	2	2.0	2.0	2.8	P	0.03	Bfl-s1	34.43	IQ PUR
IQ Megalit	EN 649	610 x 610	2	2.0	2.0	2.7	T	0.02	Bfl-s1	34.43	IQ PUR
IQ Eminent	EN 649	-	2	2.0	2.0	3	P	0.03	Bfl-s1	34.43	IQ PUR
Linoleum Veneto xf	EN 548	-	2	2.5	2.5	3		0.08	Cfl-s1	34.42	XF Surface Protection

Slip Resistant Floorcoverings	Manufacturing Standard	Tiles (mm)	Sheet Width (m)	Thickness (mm)	Weight (kg/m ²)	Abrasion Class EN660-2	Abrasion Class EN660-2	Slip Resistance			PUR Reinforcement
								Surface Roughness	DIN 51130	Wear Classification EN685	
Safetred Dimension	EN 13845 - Esf	-	2	2.0	3.0	<10% particle loss	>36	> 20μ	R10	34.43	Safety Clean XP
Safetred Wood	EN 13845	-	2	2.0	3.1	<10% particle loss	>36	> 20μ	R10	34.43	Safety Clean XP
Safetred Naturals	EN 13845	-	2	2.0	3.1	<10% particle loss	>36	> 20μ	R10	34.43	Safety Clean XP
Safetred Universal	EN 13845 - Esf	-	2	2.5	3.1	<10% particle loss	>45	> 35μ	R11	34.43	Safety Clean XP
Safetred Universal Plus	EN 13845 - Esf	-	2	2.5	3.8	<10% particle loss	>45	> 35μ	R11	34.43	Safety Clean XP
Safetred Spectrum	EN 13845 - Esf	500 x 500	2	2.0	3.1	<10% particle loss	>36	> 20μ	R10	34.43	Safety Clean XP
Granit Safe T	EN 649	-	2	2.0	3.0	P			R10	34.43	Safety Clean XP
Safetred Aqua	EN 13845 - Esb	-	2	2.0	3.0	<10% particle loss	>36	> 30μ	R11	23.32	Safety Clean XP
Granit Multisafe	EN 649	-	2	2.5	3.06	P			R10	31	-
Eclipse Aquasafe	EN 649	-	2	2.5	3.2	P			R10	31	-

Heterogenous Floorcoverings	Manufacturing Standard	Tiles (mm)	Sheet Width (m)	Thickness (mm)	Wear Layer Thickness (mm)	Weight (kg/m ²)	Abrasion Class EN660-2	Indentation (mm) EN433	Thermal Conductivity (m ² K/W)	Wear Classification EN685	PUR Reinforcement
Tapiflex Housing	EN 651	330 x 330	2	3.3	0.3	2.8	T	0.22	0.05	23.31	Top Clean XP
Tapiflex Excellence 65	EN 651	-	2	3.5	0.65	3.2	T	0.15	0.05	34.42	Top Clean XP
Tapiflex Essential 50	EN 651	-	2	3.0	0.5	3.1	T	0.1	0.5	33.42	Top Clean XP
I D Premier	EN 649	Tiles/Plank various sizes		2.5	0.55 / 0.7	3.9	T	0.5	0.3	34.42	Top Clean XP
Acczent Excellence 80	EN 649	-	2	2.0	0.8		T	0.5	0.3	34.42	Top Clean XP

Static Control Floorcoverings	Manufacturing Standard	Tiles (mm)	Sheet Width (m)	Thickness (mm)	Wear Layer Thickness (mm)	Weight (kg/m ²)	Abrasion Class EN660-2	Indentation (mm) EN433	Electrical Resistance (Ohms)	Wear Classification EN685	PUR Reinforcement
Toro SC	EN 649	610 x 610	2	2.0	2.0	3.0	P	0	5x 10 ⁴ - 1x 10 ⁶	34.43	IQ PUR
Granit SD	EN 649	610 x 610	2	2.0	2.0	3.0	P	0	R _t <10 ⁸	34.43	XR PUR
Eclipse SD	EN 649	-	2	2.0	2.0	3.1	P	0	R _t <10 ⁸	34.43	XR PUR

As Tarkett operate a programme of continuous product development, we reserve the right to amend the specification of our products without prior notice.

Tarkett Limited
Dickley Lane
Lenham
Maidstone
Kent ME17 2QX

Tel : 01622 854040
Fax : 01622 854500

Email : uksales@tarkett.com
Website : www.tarkett.co.uk



THE ULTIMATE
FLOORING EXPERIENCE